


Project: Project 1
Owner: customerservice
Site: Site of Interest 1

Sample: Sample 1
Type: Default
ID: sample 1 upper left junction



Spectrum processing :
No peaks omitted

Processing option : All elements analyzed (Normalised)
Number of iterations = 3

Standard :
O SiO2 1-Jun-1999 12:00 AM
Al Al2O3 1-Jun-1999 12:00 AM
Si SiO2 1-Jun-1999 12:00 AM

Element	App Conc.	Intensity Corrn.	Weight%	Weight% Sigma	Atomic%
O K	26.63	2.3360	2.28	0.11	3.82
Al K	523.30	1.3480	77.66	0.22	77.06
Si K	112.44	1.1215	20.06	0.21	19.12
Totals			100.00		